



PTFE H60 white sealing (I274)

This is a powerful sealant, and it's another amazing product of Ambro-Sol "Adhesive" line. It can be used in presence of water, compressed air, oils, oxygen and different chemical products. It has an high elasticity and it's waterproofing, thanks to PTFE.



HOW TO USE: The parts to be treated must be cleaned and degreased. Apply a bead of sealant at the end of the male screw and screw it, remove excess adhesive with a cloth. The pieces can be handled without affecting the polymerization after 15-30 minutes, depending on the game. The adhesive hardens completely within 6 hours. The polymerization may vary according to temperature and humidity.

Quantity	75 g
Barcode	EAN 13: 8034108892757
Box / Case	12 pz

PTFE H60 WHITE SEALING – Suitable for sealing threaded fittings with gas, compressed air, water, oils, hydrocarbons, oxygen seals and many chemicals. It replaces hemp, PTFE rolls and seals. The addition of PTFE provides greater elasticity and impermeability to the polymerized film. Medium-low resistance to removal.

Technical Specifications:

Aspect	Plastic bottle with measuring cup
Color	yellow
Odour	Characteristic of solvent
Relative density	at 20°C 1,154 g/ml
Flash point	> 100° C
Viscosity at 23°C	Aprox. 60.000 mPa s (Brookfield RVT)
Maximum thread diameter	Ask the Ambro-Sol table
Filling capacity	0,50 mm
Resistance force of torsion	6-13 N/mm ² ISO 10964
1)Unscrewing resistance	Break - 15-20 N/mm
2)Unscrewing resistance	Residual - 10-15 N/mm
Operating temperature	-55°C - +150°C
1)Hardening time	Handling: 15-30 min.
2)Hardening time	Final: 12 hours
Certificate EN 751-1	For drinking water and gas facilities

MODALITY OF STORAGE

Before using: stock the product in a dry location and don't stock it with a temperature under 5°C and over 35°C, after the use, keep containers closed. In the original package, the product can be conserved for 24 months.

After the first usage: conserve in a fresh and dry location, away from hot spring. Keep out of reach of children.

This information, even if reliable, must be considered only approximate. We are not responsible for the wrong use of the product, or the violation of any license. Before using, the users should verify the suitability of the product for its specific use.

BEFORE USE, CONSULT THE SAFETY DATA SHEET OF THE PRODUCT