



Acrylic Light Zinc 400 ml (Z362)

ACRYLIC LIGHT ZINC - Based on acrylic resins, this cold galvanizing agent produces a coating that protects all metal surfaces from oxidation. Light gray finish. An alternative product to the synthetic zinc based on raw materials that generate low environmental emissions and are not harmful to the user.



Technical Specifications:

Quantity	400ml
Box / Case	12 pcs
Barcode	EAN 13: 8050038873215
Aspect	Tin-Plate can containing under pressure fluid
Physical state	Pigmented liquid in aerosol
Flash point	Und. 0° C extremely flammable
Pressure	at 20°C 5,5 bar
Relative density	at 20°C 0,70 ÷ 0,74 g/ml
Propellant	LPG
Chemical nature	Acrylic resin with inhibiting pigment of corrosion based of zinc dust
Colour	Aluminum / light grey
Odour	Characteristic of solvent
Resistance temperature	100°C (peak of 120°C)
Dry film	16,85%
Metal in dry film	7,10%
Zinc in dry film	1,20%
Coverage	2 mq
Drying times = 20°C	Out dust: 10 min Dry to touch: 20 min Dry in depth: 6 hours Overpainted after 24 hours

APPLICATION FIELDS:

Surfaces in metal as iron, aluminum, steel. Protection of ferrous metallic structures, pipelines, eaves, enclosures, job tools etc.

HOW TO USE: Carefully clean the surface to be treated, eliminating encrustations and traces of rust with synthetic thinner. If necessary, sand with abrasive paper. Turn the can upside-down and shake well until the marbles move freely inside. To avoid drip-ping apply twice from a distance of about 20-30 cm. Once finished, spray for 2-3 seconds with the can upside-down to clean the valve and allow for future use.

MODALITY OF STORAGE

Before using: stock the product in a dry location and don't stock it with a temperature under 5°C and over 45°C, after the use, keep containers closed. In the original package, the product can be conserved for 24 months (warranty). The product doesn't expire.

After the first usage: conserve in a fresh and dry location, away from hot spring. Keep out of reach of children.

This information, even if reliable, must be considered only approximate. We are not responsible for the wrong use of the product, or the violation of any license. Before using, the users should verify the suitability of the product for its specific use.

BEFORE USE, CONSULT THE SAFETY DATA SHEET OF THE PRODUCT